



REFRACOL 12 A

SPECIFICATIONS

TYPE OF PRODUCT	: Refractory cement.
PRESENTATION	: Ready mixed pasty product
PACKING	: in 25 kg plastic or metallic drums
CLASS	: PRE Class B
MAIN COMPONENTS	: Silica.
PYROMETRIC CONE	: 1 350°C
MAXIMUM USE TEMP	: 1.260°C.
MAXIMUM GRAIN SIZE	: 0,5 mm.
BOND SYSTEM	: Air Setting.
VOLUMIC INSTALL WEIGHT	: 1,9 T/m ³
STORAGE CONSERVATION	: 6 months in a temperate room.
INSTALLATION	: By trowelling.

CHEMICAL ANALYSIS

Al ₂ O ₃	12/14 %
SiO ₂	78/81 %
Fe ₂ O ₃	0,35 %

GENERAL APPLICATION

GRADING	: < 7 % over 0,5 mm
---------	---------------------

USE

Gluing ceramic fibbers and grouting insulate bricks, coating on insulating material.

DIRECTIONS FOR USE

The REFRACOL 12 A cement can be used directly from the drum. After some months of storage, It is possible that a little segregation may be appeared. So, to find again the initial cement presentation, you have just to mix it without throwing the liquid on the top of the drum.

The 01/12/03 Ref.: 157uk/C.

The above details of our products are based on our present state of knowledge and our experience. Due to multiplicity of conditions of application, these informations should not exempt user from doing one's own controls and tests and are therefore given without any guarantee.