



REFRACOL 8

SPECIFICATIONS

TYPE OF PRODUCT	:	Air-setting mortar (jointing material).
CLASS	:	PRE Class B
PYROMETRIC CONE	:	1.700°C
MAIN COMPONENT	:	Kerphalite
MAXIMUM GRAIN SIZE	:	0,2 mm
BOND SYSTEM	:	Chemical
PACKING	:	25 kg plastic or 30 kg metallic drums
PRESENTATION	:	Pasty ready mixed
SPECIFIC GRAVITY	:	2,0
STORAGE CONSERVATION	:	6 months (room temp)
INSTALL METHOD	:	By trowelling

CHEMICAL ANALYSIS

Al ₂ O ₃	43	%
SiO ₂	51	%
Fe ₂ O ₃	0,8	%

PHYSICAL CHARACTERISTICS

GRADING	:	< 5 % over 0,2 mm.
---------	---	--------------------

The 01/05/26 Ref.:112/C

The above details of our products are based on our present state of knowledge and our experience. Due to multiplicity of conditions of application, these informations should not exempt user from doing one's own controls and tests and are therefore given without any guarantee.